



Gold Leaf German

Monarch

Monarch gold leaf average thickness is 0.36 to 0.5 microns.



Fine Gold 24kt ◆
MO24.00FG AW=19g
100% GOLD



Rosanoble 23³/₄kt ◆
MO23.75RN AW=19g
99% GOLD



Dukaten 23¹/₂kt ◆
MO23.50DK AW=18g
97.8% GOLD



Red Gold 23¹/₂kt ◆
MO23.50RG AW=18g
97.5% GOLD



23kt ◆
MO23.00GL AW=16g
MO23.00SF AW=16g
MO23.00DB AW=18g
96% GOLD



Dark 22³/₄kt ◆
MO22.75DD AW=16g
95% GOLD



Dark 22¹/₂kt
MO22.50DD AW=15g
93.5% GOLD



22kt ◆
MO22.00GL AW=16g
MO22.00SF AW=16g
MO22.00DB AW=18g
92% GOLD



French Pale 22kt
MO22.00FP AW=15g
91.5% GOLD



Moon Gold 21kt ◆
MO21.00MG AW=19.5g
91% GOLD



Lemon 18kt ◆
MO18.00LE AW=14g
75% GOLD



Pale 16kt ◆
MO16.00PL AW=15g
64% GOLD



White 13.25kt
MO13.25WH AW=16g
55% GOLD



White 12kt ◆
MO12.00WH AW=16g
50% GOLD



White 9kt ◆
MO9.00WH AW=16g
37.5% GOLD



Silver ◆
MO00.00SV AW=40
MO00.00ST AW=20
100% SILVER

Loose leaf oil gilded on white paper. The ◆ indicates leaf that is also available in patent form.
AW = Average total weight (gold + alloy) indicated in grams per 1000 leaves.